



# SELCOM

## Multiaxial Technology

**SELCOM SRL**  
 via della Torre n. 17  
**31010 FREGONA (TV) ITALY**  
 phone +39 0438 585166  
 modem fax +39 0438 585172  
 manual fax +39 0438 916049

cap. soc. EURO 101490,00  
 cod. fisc. e p.i. IT 02369430265  
 trib. Treviso n. 33642 reg. soc.  
 c.c.i.a.a. Treviso n. 206094  
 M. estero TV 028944  
 E-mail: [info@selcom-srl.com](mailto:info@selcom-srl.com)

**MULTIAXIAL TECHNOLOGY (NCF)**  
 unidirectional & stitched multiaxial fabrics in  
 glass, carbon, aramid... and hybrids for the  
 composite industry

internet: [www.selcom-srl.com](http://www.selcom-srl.com)

## Technical Data Sheet

PRODUCT NAME EBX600	Code 01200000620
Biaxial fabric $\pm 45^\circ$ in "E" glass	

layers	angle tolerance	fiber	plan	tex	areal weight	areal weight
					gr/m <sup>2</sup>	tolerance
0°	-	Polyester yarn	L6	8,1	8	$\pm 3\%$
+ 45°	$\pm 1^\circ$	E glass : PPG Roving 2002	L6	300	306	$\pm 3\%$
- 45°	$\pm 1^\circ$	E glass : PPG Roving 2002	L6	300	306	$\pm 3\%$
TOTAL gr/m <sup>2</sup>					620	$\pm 3\%$

### Characteristics for fabric

lunghezza rotolo - standard roll length:	mtl 50 $\pm$ 1 mtl
larghezza rotolo - standard roll width:	mm 1270 $\pm$ 10 mm
peso netto rotolo - net roll weight:	Kg. 40 $\pm$ 3 %
tolleranza sulla grammatura - areal weight tolerance:	$\pm 3\%$ ( $\pm 19$ gr/m <sup>2</sup> )
grammatura teorica - theoretical areal weight:	gr/m <sup>2</sup> 620
identificazione rotolo - ident roll:	<b>EBX600</b>
tipo di legatura - knitting type:	catenella - pillar
filo di legatura - stitch yarn:	polyester, texturated, 8,1 tex

### Characteristics for filament yarn

tipo fibra - type:	PPG Roving 2002
binder content :	0.55 - 0.65 % ( nominal )
produttore - manufacturer:	PPG Industries
densità volumetrica - volumetric density:	gr/cm <sup>3</sup> 2.59 - 2.62
diamentro filamento - filament diameter:	$\mu$ m 14 ( 300 tex )
resistenza a trazione - tensile strength:	Mpa 1900 - 2400 ( ASTM D-2343 ) *
modulo a trazione - tensile modulus:	Gpa 69 - 76 ( ASTM D-2343 ) *
allungamento a rottura - elongation at break:	3.5 - 4 %

\* According to ASTM D-2343. All these informations can be used for material selection purposes only.  
 Fregona lì 02/12/14

Quality Assurance  
 Ing. Giovanni Fardin

NB : THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE



**TYPE APPROVED PRODUCT - CERTIFICATE NO. K-5807**

### Confidentiality Statement

The information, data, and charts embodied in this Technical Data Sheet (TDS) are strictly confidential and are supplied on the understanding that they will be held confidentially and not disclosed to third parties without the prior written consent of Selcom srl with registered office in 31010 Fregona (TV) ITALY-Via Della Torre no. 17 -For further info, please contact Selcom srl at [info@selcom-srl.com](mailto:info@selcom-srl.com) or fax to no. +39 0438 58 51 72 / 91 60 49 SELCOM Srl is a weaver of technical textiles from continuous filaments (rovings). All information supplied by or on behalf of SELCOM Srl in relation to its products, whether in the nature of data, recommendations or otherwise, has been given in good faith and in compliance with technical and commercial information supplied by raw materials (fibre) manufacturers. All information aforementioned are supported by its own experience and believed reliable but SELCOM Srl declines all responsibility in respect of the application, processing or use of the aforementioned information or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. SELCOM Srl believes that it is the user that shall determine the suitability of a product for its end-use and the user that assures all liability in connection therewith. M10-1-02.DOC Ed.01-Rev.00-12.05.10

