TECHNICAL DATASHEET

SAP No. **30009055** **Article Description** **X-E-302g/m²-1270mm**

Textile Structure 7008669 **SAERTEX®**

ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
4	45 °	145 g/m²	+/- 5,0 %	E-glass 200 TEX
3	90 °	4 g/m²	+/- 5,0 %	E-glass 68 TEX
2	0 °	2 g/m²	+/- 5,0 %	E-glass 68 TEX
1	-45 °	145 g/m²	+/- 5,0 %	E-glass 200 TEX
Stitching		6 g/m²	+/- 1 g/m²	PES [Polyester] 76 dtex

Fiber input can be determined individually

FURTHER CHARACTERISTICS

Gauge	5,0	Stitching pattern	warp	Width (nominal)	1270 mm
Stitch length	3,00 mm	Total tolerance	+/- 5,2 %	Total areal weight	302 g/m²

Labelling (Standard) Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

Packaging (Standard) Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

Storage With original packaging: No moisture recommendation and direct sunlight.
To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.